

CHARTE DE RÉSISTANCE AUX PRODUITS CHIMIQUES APPENDIX – CHEMICAL RESISTANCE CHART

LE GUIDE DE RESISTANCE AUX PRODUITS CHIMIQUE GOODYEAR DOIT ETRE UTILISE UNIQUEMENT A TITRE DE GUIDE

- A** Le produit chimique devrait avoir peu d'effet, sinon aucun, sur le tuyau. Le tuyau peut être utilisé pour le service continu. Les changements dans les conditions de travail, tels que la concentration du produit chimique ou la température, peuvent avoir un effet sur le rendement du tuyau et causer sa détérioration.
- B** Le tuyau peut être utilisé pour le service continu ou intermittent ; cependant, les propriétés du tuyau seront modifiées par l'exposition aux produits chimiques. Les changements dans les conditions de travail, tels que la concentration du produit chimique ou la température, peuvent avoir un effet sur le rendement du tuyau et causer sa détérioration.
- X** Le tuyau ne doit pas être utilisé avec ce produit chimique.
- I** Données insuffisantes ou non disponibles pour ce produit chimique. D'autres essais sont recommandés afin de déterminer la compatibilité du produit chimique avec le tuyau.

Attention: Sauf indication contraire, les cotes attribuées aux tubes se fondent sur une concentration maximale ou une solution saturée à 100°F, dans des conditions normales d'utilisation.

Note: Les cotes s'appliquent à l'effet sur le polymère seulement. Le degré de résistance d'un composé de caoutchouc à un produit chimique, etc. Pour un composé particulier, de nombreuses catégories de polymères sont disponibles et peuvent modifier la résistance du composé aux produits chimiques.

CE GUIDE DE RÉSISTANCE AUX PRODUITS CHIMIQUES REMPLACE TOUS LES RENSEIGNEMENTS PUBLIÉS ANTERIEUREMENT CONCERNANT LES COTES DE RÉSISTANCE DES TUYAUX GOODYEAR AUX PRODUITS CHIMIQUES.

THE GOODYEAR CHEMICAL RESISTANCE CHART IS TO BE USED AS A GUIDE ONLY

- A** The chemical is expected to have minor or no effect on the product. Product may be used for continuous service. Changes in working conditions, such as concentration of the chemical or temperature, may affect product performance and cause degradation of the product.
- B** The product may be used for continuous or intermittent service, however the product properties will be affected by exposure to the chemical. Changes in working conditions, such as concentration of the chemical or temperature, may affect product performance and cause degradation of the product.
- X** The product should not be used with this chemical.
- I** Insufficient or no data available for this chemical. Further testing is recommended to determine compatibility or the chemical with the product.

Caution: Unless otherwise specified, the ratings applied to tube stocks are based on fully concentrate or saturated solutions at 100°F under normal service conditions.

Note: Hose ratings are for the effect on the polymer only. The degree of resistance of a rubber compound to a specific chemical depends on many variables such as temperature, concentration, length of exposure, stability of chemical, etc. For a specific compound's chemical resistance.

THIS CHEMICAL RESISTANCE CHART SUPERSEDES ALL PREVIOUSLY PUBLISHED INFORMATION REGARDING GOODYEAR CHEMICAL HOSE RESISTANCE RATINGS.

**CHARTE DE RÉSISTANCE AUX PRODUITS CHIMIQUES
APPENDIX – CHEMICAL RESISTANCE CHART**

	TEMPERATURE OF F	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A																	
Acetaldehyde	100	X	B	B	X	X	X	X	I	A	A	A	A	A	B	X	T
Acetic Acid, Conc.	100	B	A	A	X	B	X	X	A	A	A	A	A	A	B	X	T
Acetic Acid, Dilute 10	150	A	B	A	X	A	X	X	A	A	A	A	A	A	I	X	TVN
Acetic Acid, Glacial	100	B	A	B	X	X	X	X	A	A	A	A	A	A	B	X	T
Acetic Aldehyde	100	X	A	B	X	X	X	X	I	A	A	A	A	A	B	X	T
Acetic Anhydride	100	X	B	A	B	X	X	X	A	A	A	A	A	A	B	X	T
Acetic Ester	100	X	B	B	X	X	X	X	B	A	A	A	A	A	A	A	TV
Acetic Ether	100	X	B	B	X	X	X	X	B	A	A	A	A	A	A	A	T
Acetic Oxide	100		B	A	B	X	X	X	A	A	A	A	A	A	B	X	T
Acetone	100	X	A	A	X	B	X	X	A	A	A	A	A	A	A	I	T
Acetone Cyanohydrin	100	X	B	A	X	X	X	X	A	A	A	A	A	I	I	I	TS
Acetyl Acetone	100	X	B	B	X	X	X	X	B	I	A	A	A	I	B	I	T
Acetyl Chloride	100	I	B	X	X	X	B	X	A	B	B	A	A	B	X	A	TV
Acetyl Oxide	100		B	A	B	X	X	X	A	A	A	A	A	A	B	X	T
Acetylene (dry)	100		A	A	A	A	A	A	A	A	A	X	A	A	I	I	TVBN
Acetylene Dichloride	100	X	B	X	X	X	A	X	I	I	A	X	A	I	A	X	TV
Acetylene Tetrachloride	100	X	B	X	X	X	A	X	I	I	A	I	A	A	X	X	TV
Acrolein	100		B	A	B	B	A	B	I	I	A	A	A	I	I	I	TV
Acrylic Acid	100		B	X	X	X	A	X	X	X	A	A	A	A	I	I	TV
Acrylonitrile	100	A	B	X	X	X	X	X	A	X	B	A	A	A	X	I	T
Alk-Tri	100		I	X	X	X	A	X	I	I	A	I	A	A	I	I	TV
Allyl Alcohol	100	X	A	A	A	A	B	A	A	A	A	A	A	A	I	A	TBN
Allyl Bromide	100	X	B	X	X	X	B	X	B	I	B	I	A	I	I	I	T
Allyl Chloride	100	X	B	X	X	X	B	X	B	X	B	I	A	A	X	X	T
Alum	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Aluminum Acetate	100	I	A	A	A	X	X	X	A	A	A	A	A	A	I	X	T
Aluminum Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVB
Aluminum Formate	100		A	B	X	X	X	X	I	I	A	A	A	I	I	I	T
Aluminum Hydroxide	150	A	A	A	B	A	X	B	A	A	A	A	A	A	I	X	T

	TEMPERATURE ° F	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
Aluminum Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Aminoethanol	100		A	A	B	B	I	B	A	I	A	A	A	A	B	I	TBN
Aminoethylethanolamine	100		A	A	B	B	I	B	A	I	A	A	A	I	I	I	T
Ammonia	-		-		-	-	-	-	-	-	-	-	-	-	-	-	-
Ammonia Cupric Sulfate	150	X	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVB
Ammonium Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Ammonium Hydroxide	150	B	A	A	B	A	X	X	A	X	A	A	A	A	X	I	TN
Ammonium Nitrate (ANFO)	150	A	-	-	-	-	-	-	-	-	-	-	-	A	B	X	TVB
Ammonium Phosphate	150	I	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Ammonium Sulfate	150	A	A	A	A	A	A	X	A	A	A	A	A	A	X	X	TVN
Ammonium Sulfide	150	A	A	A	A	A	A	X	A	A	A	A	A	A	X	X	TVN
Ammonium Sulfite	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TBN
Ammonium Thiosulfate	100	A	A	A	A	A	A	A	A	A	A	A	A	A	B	X	TVBN
Amyl Acetate	100	X	A	A	B	X	X	X	X	B	A	A	A	A	A	I	T
Amyl Alcohol	100	B	A	A	A	A	B	A	A	A	A	A	A	A	I	A	TB N
Amyl Chloride	100	X	A	X	X	X	A	X	X	X	A	B	A	A	X	I	TV
Amyl Oleate	100		A	X	X	X	I	B	I	I	A	I	A	I	I	I	T
Amyl Phenol	100	X	A	X	X	X	A	X	I	I	A	I	A	I	I	I	TV
Amyl Phthalate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Amylamine	100		A	B	X	X	X	X	B	X	A	I	A	I	I	I	T
Anethole	100		X	X	X	X	B	X	X	I	X	I	A	I	I	I	T
Anhydrous Ammonia	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Aniline	100	X	A	A	X	X	A	X	B	A	A	A	A	A	B	X	TV
Animal Grease	100	A	A	X	X	X	A	A	B	X	A	A	A	A	A	I	TVB
Animal Oils	100	A	A	B	X	X	A	A	A	X	A	B	A	A	A	I	TVB
Antimony Pentachloride	100		A	X	X	X	I	X	I	X	B	B	A	I	I	I	T
Aqua Ammonia	150	B	A	A	B	A	A	B	B	B	A	A	A	A	X	I	TV
Aromatic Spirits	100		A	X	X	X	A	X	I	X	A	I	A	A	I	I	TV
Aromatic Tar	100	X	A	X	X	X	A	X	B	X	A	I	A	I	I	I	TV
Arquads	100		A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Arsenic Acid	100	A	A	A	A	A	I	X	A	A	A	A	A	A	X	X	TV

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Arsenic Chloride	100	A	I	X	X	X	X	X	X	X	X	X	A	I	I	I	TN
Arsenic Trichloride	100	A	I	X	X	X	X	X	X	X	X	X	A	X	I	I	TN
Asphalt	500	X												A	I	I	TVN
ASTM #1 Oil	100	A	A	X	B	X	A	A	A	X	A	A	A	A	A	I	TVBN
ASTM #2 Oil	100	A	A	X	X	X	A	A	A	X	A	A	A	A	A	A	TVB
ASTM #3 Oil	100	A	A	X	X	X	A	A	A	X	A	A	A	A	A	A	TVB
B																	
Barium Carbonate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Barium Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Barium Hydroxide	150	A	A	A	A	A	B	A	A	A	A	A	A	A	X	X	TBN
Barium Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	B	A	X	TVB
Barium Sulfide	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVB
Benzal Chloride	100	X	A	B	I	I	I	X	X	I	A	I	A	B	X	I	T
Benzaldehyde	100	X	A	B	X	X	X	X	X	B	A	B	A	A	B	I	T
Benzene (Benzol)	100	X	I	X	X	X	A	X	X	X	A	I	A	A	A	A	TV
Benzene (Ligroin)	100	X	A	X	X	X	A	A	I	X	A	B	A	A	A	I	TVB
Benzene Solvent (Ligroin)	100	X	A	X	X	X	A	A	I	X	A	I	A	A	A	I	TVB
Benzoic Acid	100	A	A	B	B	X	I	I	A	B	A	A	A	B	B	X	TVN
Benzoic Aldehyde	100	X	A	B	X	X	X	X	X	B	A	I	A	A	I	B	T
Benzotrichloride	100	X	X	I	I	I	I	X	X	X	X	X	A	I	I	I	T
Benzoyl Chloride	100	X	X	I	I	I	I	X	X	X	B	X	A	B	I	I	T
Benzyl Acetate	100	X	A	A	B	X	X	X	B	I	A	B	A	B	I	I	T
Benzyl Alcohol	100		A	A	X	X	A	X	A	X	A	A	A	A	B	I	TV
Benzyl Chloride	100	X	A	X	X	X	A	X	X	X	A	I	A	A	X	X	TV
Bichromate of Soda	150	A	A	A	X	I	I	I	I	I	A	A	A	I	I	I	T
Black Sulfate Liquor	150	A	A	X	B	B	B	B	A	B	A	A	A	A	X	X	TVBN
Black Sulfate Liquor	275		X	X	X	X	X	X	A	X	X	X	A	A	X	X	T
Bleach	100	A	X	B	X	X	B	X	I	A	X	B	A	X	X	X	TV
Brine	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Bromine	100	X	X	X	X	X	B	X	I	X	X	X	A	X	X	X	TV
Bromo Benzene	100	X	B	X	X	X	B	X	X	X	X	X	A	I	I	I	TV
Bromo Toluene	100	X	X	X	X	X	B	X	X	X	X	X	A	I	I	I	T
Bromochloromethae	100	X	X	B	X	X	B	X	X	I	X	A	A	A	X	X	T
Bunker C.	100		B	X	X	X	A	A	I	X	A	B	A	A	I	I	TVB

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Bunker Oil	100		B	X	X	X	A	A	I	X	X	B	A	A	I	I	TVB
Butanol	100	X	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Butyl (Normal) Alcohol	100	X	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Butyl (Secondary) Alcohol	100	X	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Butyl Acetate	100	X	A	A	B	X	X	X	B	B	A	B	A	A	B	I	T
Butyl Acetoacetate	100	X	A	X	X	X	X	X	X	I	A	B	A	I	I	I	T
Butyl Acrylate	100	X	B	X	X	X	X	X	B	X	B	B	A	I	I	I	T
Butyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Butyl Aldehyde	100		A	B	X	X	X	X	B	X	A	B	A	X	A	X	T
Butyl Amine	100		A	B	X	X	X	X	B	X	A	B	A	A	A	I	T
Butyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
Butyl Benzl Phthalate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Butyl Bromide	100	X	B	X	X	X	B	X	X	X	B	B	A	I	I	I	T
Butyl Butyrate	100	X	B	X	X	X	X	X	X	I	B	I	A	I	I	I	TV
Butyl Carbitol	100		A	A	A	X	I	X	A	B	A	A	A	I	I	I	T
Butyl Cellosolve	100		A	A	A	X	X	X	A	A	X	A	A	A	A	X	T
Butyl Chloride	100	X	B	X	X	X	A	X	X	I	B	I	A	B	I	I	TV
Butyl Ether	100		A	X	B	X	X	B	A	X	A	A	A	A	I	I	T
Butyl Ethyl Acetaldehyde	100		A	B	X	X	X	X	I	I	A	B	A	I	I	I	T
Butyl Ethyl Ether	100		A	X	B	X	I	B	I	X	A	A	A	I	I	I	T
Butyl Phthalate	100	X	A	A	X	X	X	X	I	I	A	A	A	A	A	I	T
Butyl Stearate	100		A	X	X	X	I	A	B	X	A	B	A	A	A	A	TB
Butylate	100		A	I	I	I	I	I	I	A	I	I	I	I	I	I	I
Butyraldehyde	100		A	B	X	X	X	X	B	X	A	B	A	X	A	X	T
Butyric Acid	100	X	A	X	B	X	I	X	A	B	A	A	A	A	B	I	T
Butyric Anhydride	100		A	X	B	X	I	X	I	I	A	I	A	I	I	I	T
C																	
Cadmium Acetate	100	A	A	A	A	X	X	X	A	I	A	A	A	I	I	I	T
Calcium Acetate	100	A	A	A	A	X	X	X	A	A	A	A	A	A	I	I	TB
Calcium Aluminate	100	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Calcium Bichromate	150	A	X	A	X	I	I	I	I	I	X	I	A	I	I	I	T
Calcium Bisulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Calcium Bisulfite	150	A	A	A	A	A	A	A	A	A	I	A	A	A	X	X	TVBN

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Calcium Carbonate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Calcium Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	B	X	X	TVBN
Calcium Hydroxide (Caustic Lime)	100	A	A	A	B	A	X	B	A	A	A	A	A	A	X	X	TN
Calcium Hypochlorite	100	A	B	B	X	X	B	X	A	B	X	A	A	A	X	X	TV
Calcium Nitrate	150	A	A	A	A	A	A	A	A	A	A	A	A	B	X	X	TVBN
Calcium Silicate	150	A	A	A	A	A	A	A	A	A	A	A	A	I	A	I	TVBN
Calcium Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	I	TVB
Calcium Sulphhydrate	100		A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Calcium Sulfide	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Calcium Sulfite	150	A	A	A	A	X	A	A	A	A	A	A	A	B	B	X	TVBN
Caprylic Acid	100		A	X	B	X	I	X	A	I	A	A	A	B	I	X	T
Carbitol	100		A	A	A	X	I	X	A	A	A	A	A	B	A	X	T
Carbitol Acetate	100		A	B	B	X	I	X	I	I	A	A	A	I	I	I	T
Carbolic Acid, Phenol	100	X	A	A	X	X	A	X	A	X	A	B	A	A	B	A	TV
Carbon Dioxide	100	A	A	A	A	A	A	A	A	A	A	A	A	A	B	I	TVBN
Carbon Disulfide	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Carbon Tetrachloride	100	X	B	X	X	X	A	X	X	X	A	B	A	A	I	I	TV
Carbonic Acid	100	A	A	A	A	A	A	A	A	A	A	A	A	A	B	B	TVB
Casinghead Gasoline	100	X	B	X	X	X	A	A	B	X	B	B	A	I	I	I	TVB
Caster Oil (Castor Oil)	100	A	A	A	A	X	A	A	A	A	A	A	A	A	A	I	TVB
Caustic Potash	150	A	A	A	B	A	X	B	A	B	A	A	A	A	X	X	T
Caustic Soda	150	A	A	A	B	A	X	B	A	A	A	A	A	A	X	X	TN
Cellosize	100		A	A	X	X	I	X	I	I	A	A	A	I	I	I	T
Cellosolve	100		A	A	A	X	X	X	I	A	A	A	A	A	A	X	T
Cellosolve Acetate	100		A	B	B	X	X	X	X	B	A	A	A	A	I	X	T
Chloracetic Acid	100		A	X	X	B	X	X	A	X	A	A	A	A	X	X	T
Chlorinated Solvents	100	X	B	X	X	X	A	X	B	X	A	I	A	B	X	A	TV
Chlorine (Dry) (Gas)	-	A	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Chlorine (Wet)	100	X	X	X	X	X	B	X	X	X	X	X	A	X	X	X	TV
Chloroacetone	100	X	A	I	X	X	X	X	X	X	A	I	A	A	X	X	T
Chlorobenzene	100	X	B	X	X	X	A	X	X	X	A	B	A	A	B	I	TV
Chlorobenzol	100		A	X	X	X	A	X	I	X	A	B	A	A	B	I	TV
Chlorobutane	100	X	X	X	X	X	A	X	X	I	X	I	A	I	I	I	TV

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
Chloroethylbenzene	100	X	A	X	X	X	A	X	I	X	A	I	A	I	I	I	TV
Chloroform	100	X	B	X	X	X	B	X	X	X	X	B	A	A	B	I	TV
Chloropentane	100	X	A	X	X	X	A	X	X	X	A	I	A	A	X	I	TV
Chlorophenol	100	X	A	X	X	X	B	X	X	X	X	B	A	I	I	I	TV
Chloropropanone	100	X	A	I	X	X	X	X	X	X	A	I	A	I	I	I	T
Chlorosulfonic Acid	100	B	X	X	X	X	X	X	I	X	X	X	A	B	X	X	T
Chlorothene	100	X	X	X	X	X	A	X	I	X	A	I	A	A	I	I	TV
Chlorotoluene	100	X	X	X	X	X	A	X	X	X	X	I	A	A	I	I	TV
Chlorpyrifos	100		I	I	I	I	I	I	I	X	I	I	I	I	I	I	I
Chromic Acid 25%	100	B	B	X	B	X	I	X	A	X	X	B	A	B	X	X	TV
Coal Oil	100		A	X	X	X	A	A	A	X	A	A	A	A	X	A	TVB
Coal Tar	100		A	X	X	X	A	X	B	X	A	A	A	A	I	I	T
Coal Tar Naptha	100		A	X	X	X	A	X	B	X	A	A	A	A	A	I	TV
Copper Chloride	100	A	A	A	A	X	A	A	A	A	A	A	A	X	X	X	TVBN
Copper Hydrate	100	A	A	A	B	X	X	B	I	I	A	A	A	I	I	I	TB
Copper Hydroxide	100	A	A	A	B	X	X	B	I	I	A	A	A	I	I	I	TB
Copper Nitrate	100	A	A	A	A	X	A	A	A	A	A	A	A	A	X	X	TVBN
Copper Nitrite	100	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVB
Copper Sulfate	100	A	A	A	A	X	A	A	A	A	A	A	A	A	X	X	TVBN
Copper Sulfide	100	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVB
Creosols	100	X	A	A	X	X	A	X	A	X	A	B	A	A	I	X	TV
Creosote	100	X	A	X	X	X	A	B	I	X	A	B	A	A	I	I	TV
Cresylic Acid	100		A	A	X	X	I	X	X	X	A	I	A	A	B	X	TV
Crotonaldehyde	100		A	A	X	X	X	X	A	I	A	A	A	I	I	I	T
Crude Oil	100	A	A	X	X	X	A	A	B	X	A	B	A	A	A	I	TVB
Cumene	100		A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
Cupric Carbonate	100	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVBN
Cupric Chloride	100	A	A	A	A	X	A	A	A	A	A	A	A	B	X	I	TVBN
Cupric Nitrate	100	A	A	A	A	X	A	A	A	A	A	A	A	B	I	I	TVBN
Cupric Nitrite	100	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVB
Cupric Sulfate	100	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVBN
Cyclohexane	100	X	A	X	X	X	A	B	A	X	A	B	A	A	B	X	TV
Cyclohexanol	100	X	A	X	X	X	B	B	A	X	A	B	A	A	X	X	TVB
Cyclohexanone	100	X	A	X	X	X	X	X	X	X	A	B	A	A	I	I	T

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Cyclopentane	100		A	X	X	X	A	B	B	X	A	B	A	I	I	I	TVN
Cyclopentane, methyl	100	A	A	X	X	X	A	B	I	X	A	B	A	I	I	I	TV
Cyclopentanol	100	A	A	X	X	X	B	B	A	X	A	A	A	I	I	I	TVB
Cyclopentanone	100	A	A	X	X	X	X	X	X	X	A	B	A	I	I	I	T
D																	
D.D.T. in Kerosene	100	X	A	X	X	X	A	A	A	X	A	B	A	I	I	A	TVB
D.M.P.	100		X	X	X	X	X	X	X	X	X	A	A	A	I	I	TV
Decalin	100	B	X	X	X	X	A	X	X	X	A	X	A	I	I	I	TV
Decanol	100	B	A	A	A	X	B	A	A	A	A	A	A	I	I	I	TB
Decyl Alcohol	100	A	A	A	A	X	B	A	A	A	A	A	A	I	I	I	TB
Decyl Aldehyde	100		A	X	X	X	X	X	I	I	A	B	A	I	I	I	T
Decyl Butyl Phthalate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Denatured Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	B	A	TB
Diacetone Alcohol	100	A	A	A	B	B	X	X	A	X	A	A	A	A	I	I	T
Diamyl Phenol	100	X	A	X	X	X	A	X	A	X	A	I	A	I	I	I	TV
Diamylamine	100		A	A	X	B	I	B	A	I	A	B	A	I	I	I	TB
Diamylene	100		A	X	X	X	A	X	B	X	A	B	A	I	I	I	TV
Dibenzyl Ether	100		A	B	X	X	I	X	X	X	A	B	A	A	A	X	T
Dibromobenzene	100	X	B	X	X	X	A	X	I	X	A	I	A	I	I	I	TV
Dibutyl Amine	100	X	A	X	X	B	X	B	A	X	A	A	A	I	I	I	T
Dibutyl Ether	100		A	X	B	X	X	X	A	X	A	A	A	A	A	X	T
Dibutyl Phthalate	100	X	A	A	X	X	X	X	X	A	A	A	A	A	A	I	TV
Dibutyl Sebacate	100	X	A	A	X	X	X	X	B	X	A	I	A	I	I	I	TV
Dicalcium Phosphate	100	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Dicamba	100		A	I	I	I	I	I	I	A	A	I	A	I	I	I	T
Dichloroacetic Acid	100		A	X	X	B	X	X	B	I	A	I	A	I	I	I	T
Dichlorobenzene	100	X	A	X	X	X	A	X	X	X	A	B	A	A	B	I	TV
Dichlorobutane	100	X	A	X	X	X	A	X	X	X	A	I	A	I	I	I	TV
Dichlorodifluoromethane	100	X	I	X	X	X	B	B	I	X	I	X	A	I	I	I	TVB
Dichloroethane	100	X	A	X	X	X	A	X	X	X	A	A	A	I	A	I	TV
Dichloroethyl Ether	100	X	A	X	X	X	I	X	B	X	A	B	A	I	I	I	T
Dichloroethylene	100	X	X	X	X	X	A	X	I	I	X	X	A	I	A	X	TV
Dichlorohexane	100	X	A	X	X	X	A	X	X	X	A	A	A	I	I	I	TV
Dichloromethane	100	X	A	X	X	X	A	X	X	X	A	A	A	A	B	I	TV

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
Dichloropentane	100	X	A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
Dichloropropane	100	X	A	X	X	X	A	X	X	X	B	I	A	A	X	I	TV
Diesel Oil	150	B	A	X	X	X	A	A	A	X	A	B	A	A	A	I	TVB
Diethanol Amine	100		A	A	X	B	I	B	A	I	A	A	A	A	I	I	T
Diethyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
Diethyl Carbinol	100		A	A	A	A	B	A	I	I	A	A	A	I	I	I	TBN
Diethyl Ketone	100	X	A	B	X	X	X	X	X	X	A	B	A	I	I	I	T
Diethyl Oxalate	100	X	A	B	X	B	I	X	A	X	A	B	A	I	I	I	T
Diethyl Phthalate	100	X	A	A	X	X	X	X	B	X	A	B	A	I	I	I	T
Diethyl Sebacate	100	X	A	A	X	X	X	X	B	X	A	B	A	A	A	I	T
Diethyl Sulfate	100		A	B	X	X	X	X	A	I	A	A	A	X	I	I	TN
Diethyl Triamine	100		A	A	X	B	I	B	A	I	A	A	A	I	I	I	TB
Diethylamine	100	I	A	A	X	B	I	B	B	B	A	B	A	A	I	X	TB
Diethylene Dioxide	100		A	B	X	X	X	X	B	A	A	A	A	X	X	X	T
Diethylene Glycol	100	B	A	A	A	A	A	A	X	A	A	A	A	A	B	A	TVBN
Diethylene Triamine	100		A	A	X	B	I	B	A	I	A	A	A	I	I	X	T
Dihydroxydiethyl Ether	100		A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Dihydroxyethyl Amine	100		A	A	X	B	I	B	A	I	A	A	A	I	I	I	TB
Diisobutyl Ketone	100	X	A	B	X	X	X	X	I	B	A	B	A	I	I	I	T
Diisobutylene	100		A	X	X	X	A	A	X	X	A	B	A	A	I	I	TVB
Diisooctyl Adipate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Diisooctyl Phthalate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Diisocyanate	100		X	X	X	X	X	X	X	X	X	B	A	I	I	I	T
Diisodecyl Adipate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Diisodecyl Phthalate	100		A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Diisopropanol Amine	100		A	A	X	B	I	B	I	I	A	B	A	I	I	I	TB
Diisopropyl Amine	100	X	A	A	X	B	I	B	I	I	A	B	A	I	I	I	TB
Diisopropyl Ether	100		A	X	B	X	I	B	I	X	A	B	A	A	I	I	TB
Diisopropyl Ketone	100	X	A	B	X	X	X	X	I	B	A	B	A	A	A	I	T
Dilauryl Ether	100		A	I	B	X	I	B	I	I	A	B	A	I	I		TB
Dimethyl Amine	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Dimethyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	A	I	I	TV
Dimethyl Ether	100		A	X	B	X	I	B	I	X	B	B	A	I	I	I	TB

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
<i>Dimethyl Ketone</i>	100	X	A	A	X	B	X	X	A	A	B	A	A	A	A	I	T
<i>Dimethyl Phenol</i>	100		A	X	X	X	A	X	I	X	A	A	A	I	I	I	TV
<i>Dimethyl Phthalate</i>	100	X	A	A	X	X	X	X	A	B	A	A	A	A	I	I	TV
<i>Dimethyl Sulfate</i>	100		A	B	X	X	X	X	A	I	A	A	A	I	I	I	T
<i>Dimethyl Sulfide</i>	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
<i>Dimethyl Carbinol</i>	100		A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
<i>Dinitrobenzene</i>	100	X	A	X	X	X	A	X	I	I	A	B	A	I	I	I	TV
<i>Diocetyl Adipate</i>	100	X	A	A	X	X	X	X	X	B	A	I	A	I	I	I	T
<i>Diocetyl Amine</i>	100		A	A	X	B	I	B	I	I	A	B	A	I	I	I	T
<i>Diocetyl Phthalate</i>	100	X	A	B	X	X	A	X	X	X	A	A	A	A	I	I	TV
<i>Diocetyl Sebacate</i>	100	X	A	A	X	X	X	X	X	B	A	I	A	I	I	I	TV
<i>Dioxane</i>	100		A	B	X	X	X	X	B	X	A	A	A	A	I	I	T
<i>Dioxolane</i>	100		A	X	X	X	I	X	B	X	A	B	A	I	I	I	T
<i>Diphenyl Phthalate</i>	100	X	A	A	X	X	X	X	I	I	A	A	A	I	I	I	T
<i>Dipropyl Ketone</i>	100	X	A	B	X	X	X	X	X	I	A	A	A	I	I	I	T
<i>Dipropylamine</i>	100		A	A	X	B	I	B	B	I	A	A	A	I	I	I	T
<i>Dipropylene Glycol</i>	100		A	A	A	A	A	A	A	I	A	A	A	I	I	I	TV
<i>Disodium Phosphate</i>	100	A	A	A	A	A	I	A	A	I	A	A	A	A	I	B	TB
<i>Divinyl Benzene</i>	100	X	A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
<i>Dodecyl Benzene</i>	100	X	A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
<i>Dodecyl Toluene</i>	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
<i>Dow-Per</i>	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
<i>Dowtherm A</i>	100		A	I	X	X	A	X	X	X	A	A	A	I	A	I	TV
<i>Dowtherm E</i>	100		A	X	X	X	A	X	X	X	A	A	I	I	X	I	V
<i>Dowtherm SR-1</i>	100		A	A	A	A	A	A	I	I	A	A	A	I	I	I	TVB
E																	
<i>Endolene</i>	100		I	I	I	I	I	I	I	I	I	I	I	I	I	I	I
<i>Epichlorohydrin</i>	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
<i>Ethanol</i>	100	A	A	A	A	A	B	A	A	A	A	A	A	A	B	A	TBN
<i>Ethanol Amine</i>	100	A	A	A	B	B	I	B	A	B	A	B	A	A	B	I	TB
<i>Ethyl Acetate</i>	100	X	A	B	X	X	X	X	B	A	A	A	A	A	A	A	T
<i>Ethyl Acetoacetate</i>	100	X	A	B	X	X	X	X	A	B	A	A	A	B	I	I	T
<i>Ethyl Acrylate</i>	100	X	A	X	X	X	X	X	B	X	B	B	A	A	A	A	T
<i>Ethyl Alcohol</i>	100	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	TVBN
<i>Ethyl Aldehyde</i>	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Ethyl Aluminum Dichloride	100		X	X	X	X	B	X	I	X	B	I	A	I	I	I	TV
Ethyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	A	A	X	TV
Ethyl Butanol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Ethyl Butyl Acetate	100	X	A	A	B	X	X	X	I	I	A	B	A	I	I	I	T
Ethyl Butyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Ethyl Butyl Amine	100		A	A	X	B	I	B	I	I	I	I	A	I	I	I	TB
Ethyl Butyl Ketone	100	X	A	B	X	X	X	X	X	I	A	A	A	I	I	I	T
Ethyl Butyraldehyde	100		A	B	X	X	X	X	X	I	A	B	A	I	I	I	T
Ethyl Chloride	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ethyl Dichloride	100	X	B	X	X	X	B	X	X	X	B	B	A	I	I	I	TV
Ethyl Ether	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ethyl Formate	100	X	A	B	X	X	X	X	A	B	A	A	A	A	I	I	TV
Ethyl Hexanol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TBN
Ethyl Hexoic Acid	100		A	X	B	X	I	X	I	I	A	A	A	I	I	I	T
Ethyl Hexyl Acetate	100	X	A	A	B	X	X	X	I	I	A	B	A	I	I	I	T
Ethyl Hexyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TBN
Ethyl Iodide	100	X	X	X	X	X	B	X	X	X	B	B	A	I	I	I	TV
Ethyl Isobutyl Ether	100	X	A	X	B	X	I	B	I	X	A	B	A	I	I	I	T
Ethyl Methyl Ketone	100	X	A	B	X	X	X	X	I	I	A	A	A	A	A	A	T
Ethyl Oxalate	100	X	A	A	X	A	I	X	A	X	A	B	A	I	I	I	TV
Ethyl Phthalate	100	X	A	A	X	X	X	X	B	I	A	I	A	I	I	I	T
Ethyl Propyl Ether	100	X	A	X	B	X	I	B	A	X	A	B	A	I	I	I	TB
Ethyl Propyl Ketone	100	X	A	B	X	X	X	X	I	I	A	A	A	I	I	I	T
Ethyl Silicate	100		A	A	I	X	I	A	A	I	A	A	A	A	I	I	TBN
Ethyl Sulfate	100		A	B	X	X	X	X	A	I	A	A	A	X	I	I	TB
Ethylamine	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ethylene Bromide	100	X	X	X	X	X	B	X	I	X	B	B	A	A	X	I	TV
Ethylene Chloride	100	X	B	X	X	X	B	X	I	X	B	B	A	A	B	I	TV
Ethylene Diamine	100		A	A	X	B	I	B	I	B	A	I	A	A	I	I	TB
Ethylene Dibromide	100	X	X	X	X	X	B	X	I	X	B	B	A	A	X	I	TV
Ethylene Dichloride	100	X	B	X	X	X	B	X	X	X	B	A	A	A	B	I	TV
Ethylene Glycol	150	A	A	A	A	A	A	A	A	A	A	A	A	A	A	I	TVBN
Ethylhexil Phosphordieth	100		I	X	X	I	I	A	A	X	X	I	I	I	I	I	B
Ex-Tri	100		A	X	X	X	A	X	I	I	A	B	A	I	I	I	TV

	TEMPERATURE OF	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE															
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
F																	
Ferric Bromide	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Ferric Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	X	X	X	TVBN
Ferric Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Ferrous Acetate	100	A	A	A	A	X	X	X	I	I	A	A	A	I	I	I	T
Ferrous Chloride	150	A	A	A	A	A	B	A	A	A	A	A	A	I	X	X	TB
Ferrous Hydroxide	100	A	A	A	B	A	X	B	I	I	A	A	A	B	I	I	TN
Ferrous Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	B	X	X	TVBN
Fluoboric Acid 65%	150		B	A	A	A	I	I	A	I	I	A	A	I	I	X	TN
Fluorine (wet)	100	X	X	X	X	X	X	X	X	X	X	X	B	X	X	X	T
Fluosilicic Acid 50%	150	A	B	A	A	A	I	I	A	I	I	A	A	A	X	X	TN
Formaldehyde 40%	100	X	A	A	A	B	B	A	A	A	A	A	A	A	B	I	TB
Formalin	100	I	A	A	A	B	A	A	A	A	A	A	A	A	B	I	TVB
Formic Acid	100	X	A	A	X	B	X	X	A	A	B	A	A	B	I	X	TV
Freon 12	100	B	A	X	X	X	B	B	I	X	B	X	A	A	I	I	TN
Freon 22	100	X	A	X	X	X	X	X	I	I	B	X	A	A	I	I	TN
Fuel A (ASTM)	100	B	B	X	X	X	A	A	I	X	B	B	A	A	A	A	TVB
Fuel B (ASTM)	100	B	B	X	X	X	A	A	I	X	B	B	A	I	I	I	TVB
Fuel Oil	100	B	A	X	X	X	A	A	X	X	B	B	A	A	A	I	TVB
Furfural	100	X	A	A	I	I	X	X	A	B	A	A	A	A	A	X	T
Furfuryl Alcohol	100		A	X	I	I	X	I	A	I	A	A	A	A	A	I	T
G																	
Gallic Acid	100		A	B	I	A	I	I	A	B	I	B	A	B	I	I	T
Gasoline	100	X	B	X	X	X	A	A	B	X	B	B	A	A	I	I	TVB
Glacial Acetic Acid	100	B	A	B	X	X	X	X	B	A	A	A	A	A	B	X	T
Gluconic Acid	100		A	X	B	X	I	X	A	I	A	A	A	X	X	A	T
Glycerin	100	A	A	A	A	A	A	A	A	A	B	A	A	A	A	A	TVBN
Glyphosate	100		A	I	I	I	I	I	I	A	I	I	I	I	I	I	I
Graffinite	100		I	X	X	X	X	A	A	X	X	I	I	I	I	I	B
Grease	100	A	A	X	X	X	A	A	I	X	B	A	A	A	A	A	TVB
Green Sulfate Liquor	150		A	A	A	A	I	A	A	A	A	A	A	A	X	X	TBS
H																	
Heptanal	100		A	X	X	X	X	X	X	I	A	I	A	I	I	I	TB
Heptane	100	A	A	X	X	X	A	A	A	X	B	B	A	A	A	I	TVB
Heptane Carboxylic Acid	100		A	X	B	X	A	X	A	I	A	A	A	I	I	I	TV

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Hexaldehyde	100		A	X	X	X	X	X	I	X	A	B	A	A	A	I	T
Hexane	100	A	B	X	X	X	A	A	B	X	B	B	A	A	A	A	TVB
Hexanol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TB
Hexyl Methyl Ketone	100	X	A	B	X	X	X	X	I	I	A	A	A	I	I	I	T
Hexylamine	100		A	B	X	X	X	X	B	I	A	B	A	I	I	I	T
Hexylene	100		X	X	X	X	A	A	I	X	X	I	A	I	I	I	TVB
Hexylene Glycol	150	B	A	A	A	A	A	A	A	I	A	A	A	A	B	A	TVBN
Hexyl-Alcohol	100	A	A	A	A	A	B	A	A	X	A	A	A	A	I	I	TB
Hi-Tri	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Hydrochloric Acid -38% Conc.	125		I	A	X	B	I	X	A	B	A	A	A	X	X	X	T
Hydrobromic Acid (37%)	150	A	B	A	A	A	I	X	A	A	I	A	A	X	X	X	TN
Hydrochloric Acid (37%)	125	B	A	A	X	B	X	X	A	B	A	A	A	X	X	X	T
Hydrofluoric Acid (10%)	125	B	A	A	A	X	I	X	A	I	A	A	A	A	X	X	TN
Hydrofluosilicic Acid	150	B	B	B	A	A	I	I	A	A	I	A	A	A	X	X	T
Hydrogen Dioxide 10%	100	A	B	X	X	X	A	X	I	I	I	I	A	A	B	X	TV
Hydrogen Dioxide over 10%	100	A	B	X	X	X	I	X	I	X	I	I	A	I	I	X	T
Hydrogen Gas	100	X		-	-	-	-	-	-	-	-	-	-	-	-	-	-
Hydrogen Peroxide 10% to 50%	100	A	B	X	X	X	A	X	A	I	I	I	A	I	B	I	TV
Hydrogen Peroxide over 50%	100	A	X	X	X	X	X	X	X	X	X	I	A	A	I	X	T
I																	
Iodine	100	X	A	I	A	I	I	I	A	I	B	I	A	I	I	X	TVB
Iron Acetate	100	A	A	A	A	X	X	X	I	I	A	A	A	I	I	I	TN
Iron Hydroxide	100	A	A	A	B	X	X	B	I	I	A	A	A	I	I	I	TN
Iron Salts	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Iron Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Iron Sulfide	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Isoamyl Acetate	100	X	A	A	B	X	X	X	I	X	A	B	A	I	I	I	T
Isoamyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	A	TBN
Isoamyl Bromide	100	X	B	X	X	X	B	X	I	X	B	I	A	I	I	I	TV

	TEMPERATURE OF F	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Isoamyl Butyrate	100	X	B	X	X	X	X	X	I	I	B	B	A	I	I	I	T
Isoamyl Chloride	100	X	X	X	X	X	B	X	I	I	X	B	A	I	I	I	TV
Isoamyl Ether	100	X	A	X	B	X	I	B	I	X	A	I	A	I	I	I	T
Isoamyl Phthalate	100	X	A	A	X	X	X	X	I	I	A	I	A	I	I	I	T
Isobutane	-																
Isobutanol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Isobutyl Acetate	100	X	A	A	B	X	X	X	B	X	A	B	A	A	B	I	T
Isobutyl Alcohol	100	A	A	A	A	A	B	X	A	A	A	A	A	A	I	I	TN
Isobutyl Aldehyde	100		A	B	X	X	X	X	B	I	A	B	A	I	I	I	T
Isobutyl Amine	100		A	B	X	X	X	X	I	I	A	B	A	I	I	I	T
Isobutyl Bromide	100		B	X	X	X	B	X	I	X	X	I	A	I	I	I	TV
Isobutyl Carbinol	100		A	A	A	A	B	A	A	A	A	A	A	A	I	A	TBN
Isobutyl Chloride	100		B	X	X	X	B	X	I	X	X	I	A	I	I	I	TV
Isobutyl Ether	100		A	X	B	X	I	X	I	X	A	I	A	I	I	I	TB
Isobutylene	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Isooctane	100	B	B	X	X	X	A	A	I	X	B	B	A	A	A	A	TVB
Isopentane	-	B															
Isophorone	100		B	A	I	I	I	X	I	A	B	B	A	B	A	I	T
Isopropanol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TVB
Isopropanol Amine	100		A	A	X	B	X	B	I	I	A	B	A	I	I	I	TB
Isopropyl Acetate	100	X	A	A	X	X	X	X	B	X	A	A	A	A	I	I	T
Isopropyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TBN
Isopropyl Amine	100		A	B	X	X	X	X	I	I	A	B	A	I	I	I	T
Isopropyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	I	I	I	TV
Isopropyl Chloride	-	X															
Isopropyl Ether	100		A	X	B	X	I	X	I	X	A	B	A	A	I	I	TB
Isopropyl Toluene	100		A	X	X	X	A	X	I	X	A	I	A	I	I	I	TV
J																	
Jet Fuels	-	X												A	A	A	TVB
K																	
Kerosene	100	B	A	X	X	X	A	B	A	X	A	A	A	A	A	I	TVB
L																	
Lauryl Alcohol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Lead Acetate	100	A	A	A	X	X	X	X	A	B	A	A	A	A	X	X	T
Lead Sulfate	150	X	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Ligroin	100		A	X	X	X	A	A	I	X	A	B	A	A	A	I	TVB
Linseed Oil	100	A	A	A	B	X	A	A	A	B	I	A	A	A	I	A	TVBN
Liquefied Natural Gas (LNG)	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Liquefied Petroleum Gas (LPG)	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Lubricating Oils	100	B	A	X	X	X	A	A	I	X	A	I	A	A	A	A	TVB
M																	
MIBK	100	X	A	X	X	X	X	X	X	X	A	B	A	X	X	X	T
M.E.K.	100	X	A	X	X	X	X	X	X	X	A	B	A	X	X	X	T
Magnesium Acetate	100	A	A	A	A	X	X	X	A	I	A	A	A	I	I	I	T
Magnesium Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVB
Magnesium Hydrate	150	A	A	A	B	A	B	B	I	I	A	A	A	A	X	I	TN
Magnesium Hydroxide	150	A	A	A	B	A	B	B	A	A	A	A	A	A	X	I	TVBN
Magnesium Sulfate	150	A	A	A	A	A	A	A	A	B	A	A	A	A	I	I	TVBN
Maleic Acid	100	A	A	X	X	X	I	X	I	I	B	I	A	A	B	X	TV
Malic Acid	150		B	I	A	A	I	I	I	I	I	I	A	A	B	X	TVBN
Manganese Sulfate	150	A	A	A	A	X	A	A	A	A	A	A	A	A	I	I	TVBN
Manganese Sulfide	150	A	A	A	A	X	A	A	A	A	A	A	A	I	I	I	TVB
Manganese Sulfite	150	A	A	A	A	X	A	A	A	A	A	A	A	A	I	I	TVB
Menthanol	100	A	A	A	A	A	X	A	A	A	A	A	A	A	I	I	TB
Mesityl Oxide	100		A	B	X	X	X	X	B	X	A	B	A	A	I	I	T
Methallyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Methyl (Wood) Alcohol	100	B	A	A	A	A	X	A	A	A	A	A	A	A	I	I	TBN
Methyl Acetate	100	X	A	A	B	X	X	X	A	A	A	A	A	A	I	I	T
Methyl Acetoacetate	100	X	A	B	X	X	X	X	A	I	A	A	A	A	I	I	T
Methyl Acetone	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Methyl Amyl Acetate	100	X	B	A	B	X	X	X	I	X	A	B	A	I	I	I	T
Methyl Amyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TBN
Methyl Amyl Carbinol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Methyl Amyl Ketone	100	X	A	B	X	X	X	X	X	I	A	B	A	I	I	I	T
Methyl Benzene	100	X	A	X	X	X	A	X	X	X	A	B	A	A	A	A	TV
Methyl Butanol	100	B	A	A	A	A	B	A	A	I	A	A	A	A	I	A	TBN
Methyl Butanone	100		A	B	X	X	X	X	B	B	A	B	A	I	I	I	T
Methyl Butyl Ketone	100	X	A	B	X	X	X	X	X	I	A	B	A	A	B	I	T

	TEMPERATURE OF F	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSYN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Methyl Carbitol	100		A	A	A	X	I	X	A	I	A	A	A	I	I	I	T
Methyl Cellosolve	100	B	A	A	A	X	I	X	A	A	A	A	A	A	B	A	T
Methyl Chloride	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Methyl Cyclohexane	100		A	X	X	X	B	X	B	X	B	I	A	I	I	I	TV
Methyl Ethyl Ketone	100	X	A	X	X	X	X	X	X	X	A	B	A	X	X	X	T
Methyl Hexanol	100		A	A	A	B	A	A	A	A	A	A	A	I	I	I	TVB
Methyl Hexanone	100		A	B	X	X	X	X	X	I	A	B	A	I	I	I	T
Methyl Hexyl Ketone	100	X	A	B	X	X	X	X	X	I	A	B	A	I	I	I	T
Methyl Isobutyl Carbinol	100		A	A	A	A	B	A	A	A	A	A	A	B	I	I	TBN
Methyl Isobutyl Ketone (MIBK)	100	X	A	X	X	X	X	X	X	X	A	B	A	X	X	X	T
Methyl Isopropyl Ketone	100	X	A	B	X	X	X	X	B	B	A	B	A	A	I	I	T
Methyl Normal Amyl Ketone	100	X	A	B	X	X	X	X	I	I	A	B	A	I	I	I	T
Methyl Propyl Carbinol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Methyl Propyl Ether	100	I	A	X	B	X	I	X	I	X	A	B	A	I	I	I	T
Methyl Propyl Ketone	100	X	A	B	X	X	X	X	B	I	A	B	A	I	I	I	T
Methyl Tertiary Butyl Ether	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
(MTBE) 100% Concentrate	100		X	X	X	X	X	X	X	X	A	B	I	I	I	I	I
Methylalyl Acetate	100	X	A	A	B	X	X	X	I	A	A	A	A	I	I	I	T
Methylalyl Chloride	100	X	A	X	X	X	X	X	X	I	B	I	A	I	I	I	T
Methyldiethanolamin	100		A	X	X	X	X	A	A	X	A	A	A	I	I	I	TB
Methylene Bromide	100	X	B	X	X	X	B	X	I	X	B	A	A	I	I	I	TV
Methylene Chloride	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Metribuzin	100		A	I	I	I	I	I	I	A	I	I	A	I	I	I	T
Mineral Spirits	100	B	A	X	X	X	B	A	I	X	A	B	A	A	A	I	TB
Monochloroacetic Acid	100		A	X	X	B	I	X	A	X	A	A	A	A	X	X	T
Monochlorobenzene	100	X	B	X	X	X	A	X	X	X	B	B	A	A	B	B	TV
Monochlorodifluoromethane	100	X	I	X	X	X	X	X	I	I	I	I	A	A	I	I	TN
Monoethanol Amine	100		A	A	X	B	I	B	A	B	A	B	A	A	B	I	TN
Monoethyl Amine	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Monoisopropanol Amine	100		A	A	X	B	I	B	I	I	A	B	A	I	I	I	TB

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Muriatic Acid	125	B	A	X	X	A	I	X	A	X	A	A	A	X	X	X	T
N																	
N/Methylpyrrolidon	100		A	X	X	X	X	X	X	X	A	I	A	I	I	I	T
Naphtha	100	B	A	X	X	X	A	A	A	X	A	A	A	A	A	I	TVBN
Naphthalene	100	X	A	X	X	X	A	X	I	X	A	I	A	A	B	I	TV
Natural Gas	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Neohexane	100		A	X	X	X	A	A	B	X	A	B	A	A	A	I	TVB
Neu-Tri	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Nickel Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	B	X	X	TVB
Nickel Nitrate	150	A	A	A	A	A	A	A	A	A	A	A	A	B	X	X	TVBN
Nickel Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TBN
Nitric Acid 25%	100		B	B	X	X	X	X	X	X	B	A	A	A	X	X	TV
Nitric Acid 37%	100		X	X	X	X	X	X	X	X	X	A	A	A	X	X	TV
Nitric Acid 40%-60%	100		X	X	X	X	X	X	X	X	X	B	A	A	X	X	TV
Nitric Acid 70%	100		X	X	X	X	X	X	X	X	X	B	A	B	X	X	T
Nitro Benzene	100	X	A	X	X	X	B	X	X	X	A	B	A	A	B	X	T
Nitrogen Gas	100	A	A	A	A	A	A	A	A	A	A	A	A	A	I	I	TVBN
Nitrous Oxide	100	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Nonenes	100		A	X	X	X	A	A	I	X	A	B	A	I	I	I	VB
O																	
Octadecanoic Acid	100		A	B	X	X	I	A	A	B	A	A	A	A	B	A	TB
Octane	100		B	X	X	X	A	A	A	X	B	B	A	B	I	B	TVB
Octanol	100	A	A	A	A	A	B	A	A	X	A	A	A	A	I	I	TBN
Octyl Acetate	100	X	A	A	A	X	X	X	X	I	A	B	A	I	I	I	T
Octyl Alcohol	100		A	A	A	A	B	A	A	X	A	A	A	A	I	I	TB
Octyl Aldehyde	100		A	X	X	X	X	X	I	I	A	I	A	I	I	I	T
Octyl Amine	100		A	B	X	X	X	X	B	I	A	B	A	I	I	I	T
Octyl Carbinol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Octylene Glycol	100		A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Oil Petroleum	100	B	B	X	X	X	A	A	A	X	A	B	A	A	A	X	TVB
Oleic Acid	100	B	A	B	X	X	I	A	A	X	A	B	A	A	B	X	TB
Oleum	100	X	X	X	X	X	X	X	X	X	X	X	A	I	X	X	TV
Organic Fatty Acids	100		A	X	X	X	X	A	A	X	A	B	A	A	I	I	TB
Orthodichlorobenzen	100	X	A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Orthodichlorobenzol	100	X	A	X	X	X	A	X	I	X	A	I	A	I	I	I	

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Orthoxylene	100		B	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Oxalic Acid	100	A	A	A	X	X	I	X	A	B	I	B	A	A	B	X	T
Oxygen	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Ozone	100	B	A	B	B	X	I	X	A	A	I	B	A	I	I	I	T
P																	
Palmitic Acid	100	B	A	A	B	X	I	A	A	B	B	B	A	A	I	X	TB
Papermakers Alum	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Paradichlorobenzol	100	X	B	X	X	X	A	X	I	X	A	I	A	I	I	I	TV
Paraffin	150	A	A	B	X	X	A	A	A	X	X	I	A	A	A	A	TVB
Paraldehyde	100		A	B	X	X	X	X	I	B	A	B	A	A	A	I	T
Paraxylene	100		A	X	X	X	A	X	I	X	A	B	A	I	I	I	TV
Pelargonic Acid	100		A	A	X	X	I	A	I	I	A	I	A	I	I	I	TB
Pentachloroethane	100	I	A	X	X	X	A	X	I	X	A	I	A	A	B	X	TV
Pentane	100	B	X	X	X	X	A	A	A	X	B	X	A	B	A	A	TVB
Pentanol	100	A	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TBN
Pentanone	100		A	B	X	X	X	X	B	I	A	B	A	I	I	I	T
Perchloroethylene	100	X	B	X	X	X	A	X	X	X	A	B	A	A	B	X	TV
Petroleum Ether (Ligroin)	100	B	A	X	X	X	A	A	A	X	A	B	A	A	A	I	TVB
Petroleum - Crude	100	B	A	X	X	X	A	A	A	X	A	B	A	A	A	X	TVB
Petroleum Oils	100	B	A	X	X	X	A	A	A	X	A	B	A	A	A	X	TVB
Phenol	125	X	A	A	X	X	A	X	A	X	A	B	A	A	B	B	TV
Phenolsulfonic Acid	100	X	X	X	X	X	X	X	A	I	B	B	A	B	I	I	T
Phenyl Chloride	100	I	A	X	X	X	A	X	X	X	A	B	A	A	B	I	TV
Phosphoric Acid 10%	150	A	A	A	A	A	X	A	A	A	A	A	A	A	X	X	TVBN
Phosphoric Acid 10-85%	100	B	A	A	A	B	X	X	A	A	A	A	A	A	X	I	TVN
Pine Oil	100		A	X	X	X	A	X	B	X	A	B	A	A	I	X	TV
Pinene	100		A	X	X	X	A	B	B	X	A	B	A	B	I	I	TV
Polyethylene Glycol	150	B	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Polypropylene Glycol	150	B	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Potassium Acetate	100	A	A	A	B	X	X	X	A	B	A	A	A	A	X	X	TB
Potassium Bisulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Potassium Bisulfite	150	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVBN
Potassium Carbonate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Potassium Chloride	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
<i>A = Peut être utilisé pour service continu</i>																	
<i>B = Peut être utilisé pour service intermittent</i>																	
<i>X = Ne pas utiliser</i>																	
<i>I = Données insuffisantes</i>																	
<i>A = May be used for continuous service</i>																	
<i>B = May be used for Intermittent service</i>																	
<i>X = Do not use</i>																	
<i>I = Insufficient data</i>																	
Potassium Chromate	150	A	B	A	X	I	I	I	A	I	B	B	A	B	I	I	TVBN
Potassium Dichromate	150	A	B	A	X	I	I	I	A	I	B	B	A	A	B	X	TVBN
Potassium Hydrate	150	A	A	A	B	A	X	B	A	B	A	A	A	A	X	I	T
Potassium Hydroxide	150	A	B	A	B	A	X	B	A	B	A	A	A	A	X	X	TN
Potassium Nitrate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	TVBN
Potassium Permanganate	100		A	A	A	A	A	B	I	I	A	A	A	A	I	I	TV
Potassium Silicate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	I	TVBN
Potassium Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	B	A	TVBN
Potassium Sulfide	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Potassium Sulfite	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Propanediol	100	A	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Propane Gas	-		-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Propanol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TVB
Propyl Acetate	100	X	A	A	B	X	X	X	B	X	A	B	A	A	I	I	T
Propyl Alcohol	100	A	A	A	A	A	B	A	A	A	A	A	A	A	I	I	TB
Propyl Aldehyde	100		A	B	X	X	X	X	X	I	A	B	A	I	I	I	T
Propyl Chloride	-	X	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Propylene Diamine	100		A	A	X	B	I	B	A	I	A	I	A	I	I	I	TB
Propylene Dichloride	100	X	B	X	X	X	B	X	X	X	B	I	A	A	X	I	TV
Propylene Glycol	100	I	A	A	A	A	A	A	A	A	A	A	A	A	I	I	TVB
Propylene Tetramer	100		A	X	X	X	X	A	A	X	A	B	I	I	I	I	B
S																	
Sea Water	100	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Sewage	100		A	X	A	X	I	A	A	A	A	A	A	A	X	I	TBN
Silicate of Soda	100	B	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Soap	100		A	X	X	X	X	A	A	X	X	I	A	A	X	X	TBN
Soda Ash	100	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Soda, Caustic	100	B	A	A	B	A	X	B	A	A	A	A	A	A	X	X	TN
Soda, Lime	100	B	A	A	B	A	X	B	A	A	A	A	A	I	I	I	TVB
Soda, Niter	100	B	A	A	A	A	A	A	A	B	A	A	A	A	B	I	TVB
Sodium Acetate	100	B	A	A	A	X	X	X	A	B	B	B	A	A	I	A	TN
Sodium Aluminate	100	A	A	A	A	A	A	A	A	A	A	A	A	A	I	I	TVBN
Sodium Bisulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Sodium Bisulfite	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NTRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
A = Peut être utilisé pour service continu B = Peut être utilisé pour service intermittent X = Ne pas utiliser I = Données insuffisantes																	
A = May be used for continuous service B = May be used for Intermittent service X = Do not use I = Insufficient data																	
Sodium Carbonate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Sodium Chloride (Brine)	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	I	TVBN
Sodium Chromate	150	A	X	A	X	I	I	I	A	I	X	I	A	A	A	A	TVBN
Sodium Dichromate	150	A	A	A	X	I	I	I	A	A	A	A	A	A	I	X	T
Sodium Hydrate	150	A	A	A	B	A	X	B	A	A	A	A	A	B	X	X	TN
Sodium Hydrochlorite (20%)	100	A	A	B	X	X	B	X	I	I	B	A	A	I	I	I	T
Sodium Hydrosulfide	100		A	X	X	X	X	A	A	X	A	I	A	I	B	I	TB
Sodium Hydroxide (50%)	150	A	A	A	B	A	X	B	A	A	A	A	A	A	X	X	TBN
Sodium Hypochlorite	100	A	B	B	X	X	B	X	A	A	X	B	A	X	X	X	TV
Sodium Nitrate	150	A	A	A	A	A	A	A	A	B	A	A	A	A	B	I	TVBN
Sodium Silicate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Sodium Sulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	B	X	TVBN
Sodium Sulfide	150	A	A	A	A	A	A	A	A	A	A	A	A	A	X	X	TVBN
Sodium Sulfite	150	A	A	A	A	A	A	A	A	B	A	A	A	A	I	I	TVBN
Sodium Sulphydrate	100		A	X	X	X	X	A	A	X	A	B	A	I	I	I	TB
Sodium Thiosulfate	150	A	A	A	A	A	A	A	A	A	A	A	A	A	I	X	TVBN
Stannic Chloride	150	A	A	A	A	A	I	A	A	A	A	A	A	X	X	X	TB
Stannic Sulfide	150	A	A	A	A	A	I	A	A	A	A	A	A	I	I	I	TBN
Stannous Chloride	150	A	A	A	A	A	I	A	A	B	A	A	A	A	X	X	TB
Stannous Sulfide	150	A	A	A	A	A	I	A	A	A	A	A	A	I	I	I	TB
Stearic Acid	100	A	A	B	X	X	I	A	A	B	A	A	A	A	B	A	TVB
Stoddards Solvent	100		A	X	X	X	A	A	A	X	A	B	A	A	A	I	TVB
Styrene	100		B	X	X	X	A	X	X	X	X	I	A	A	I	I	TV
Sulfamic Acid (>10%)	100		X	A	B	B	I	B	A	I	I	I	A	I	I	I	TVN
Sulfonic Acid	100	B	B	X	X	X	X	X	I	I	B	I	A	I	I	I	TVN
Sulfur Dioxide (Liquid)	100	X	B	B	B	I	X	I	I	I	X	I	A	A	I	I	TN
Sulfuric Acid 25%	150	A	A	A	B	B	I	X	A	A	A	A	A	I	X	X	TVN
Sulfuric Acid 93%	100	X	X	X	B	X	B	X	X	B	A	A	A	I	X	X	TV
Sulfuric Acid 93-98%	100	X	X	X	X	X	B	X	X	X	I	B	A	I	X	X	TV
Sulfuric Acid Fuming	100	X	X	X	X	X	X	X	X	X	X	X	A	I	X	X	T
Sulfurous Acid 10%	150	B	A	A	A	A	I	X	A	A	A	A	A	I	X	X	T
Sulfurous Acid 10-75%	100	X	A	A	A	A	I	X	A	A	A	A	A	I	X	X	T
Sulphonate	100		I	X	X	X	X	A	A	X	X	I	I	I	I	I	B

	TEMPERATURE OF	PLIOVIC	PLIOSYN	WEATHEREX	HYSUNITE	PURETEN	FLOSINN	CHEMIGUM	CHEMRIN	VERSIGARD	SPECIAR	APHASYN	TEFLON	316 SS	ALUMINIUM	BRASS	GASKET: T=TEFLON V=VITON B=NITRILE N=NEOPRENE
		PVC	UHMWPE	BUTYL	HYPALON	PURE GUM	VITON	NITRILE	CPE	EPDM	XLPE	XLPE MOD	TEFLON	316 SS	ALUMINIUM	BRASS	
T																	
Tall Oil	100		A	X	X	X	A	A	I	X	I	I	A	A	X	X	TVB
Tallow	150		A	X	X	X	I	A	A	X	I	I	A	A	I	A	TBN
Tannic Acid	150	B	A	A	A	A	I	B	A	X	I	I	A	A	X	I	TVBN
Tar	-	X	-	-	-	-	-	-	-	-	-	-	-	A	A	I	I
Tartaric Acid	150	A	A	A	A	A	I	A	A	A	A	A	A	A	I	A	TBN
Tergitol	100		X	I	I	I	I	I	I	I	I	I	A	I	I	I	T
Tertiary Butyl Alcohol	100	B	A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Tetrachlorobenzene	100	X	B	X	X	X	B	X	I	X	B	I	A	I	I	I	T
Tetrachloroethane	100	X	A	X	X	X	A	X	I	X	X	I	A	A	X	X	TV
Tetrachloroethylene	100	X	A	X	X	X	A	X	X	X	A	B	A	A	B	X	TV
Tetrachloromethane	100	X	A	X	X	X	A	X	X	X	X	B	A	A	I	I	TV
Tetrachloronaphthalene	100	X	B	X	X	X	B	X	I	X	X	I	A	I	I	I	T
Tetradecanol	100		A	A	A	A	B	A	A	A	A	A	A	I	I	I	TB
Tetraethylene Glycol	150	B	A	A	A	A	A	A	A	A	A	A	A	I	I	I	TVB
Tetraethylene Lead	100		X	X	X	X	A	X	X	X	X	I	A	I	I	I	TV
Tetrahydrofuran	100	X	B	X	X	X	X	X	X	X	B	X	A	A	B	X	T
THF	100	X	B	X	X	X	X	X	X	X	B	X	A	A	B	X	T
Thionyl Chloride	100		X	I	I	I	I	I	I	I	I	X	A	X	X	X	T
Tin Chloride	100	B	A	A	A	A	I	A	A	A	A	A	A	X	X	X	TVB
Tin Tetrachloride	150	B	B	A	A	A	I	A	A	A	A	A	A	X	X	X	TB
Titanium Tetrachloride	100		B	X	X	X	A	B	X	X	A	B	A	B	X	X	TV
Toluene	100	X	A	X	X	X	A	X	X	X	B	B	A	A	A	A	TV
Toluidine	100	X	X	I	I	I	I	I	I	I	I	I	A	I	I	I	T
Toluol	100	X	A	X	X	X	A	X	X	X	A	B	A	A	A	A	TV
Transformer Oil	100		X	I	I	I	I	I	I	I	I	I	A	A	I	I	T
Transmission Oil "A"	150	B	B	X	X	X	A	A	I	X	I	I	A	A	A	A	TVB
Tributoxy Ethylsulphate	100		I	A	X	X	A	X	X	A	X	I	I	I	I	I	V
Tributyl Amine	100		A	A	X	B	I	B	A	I	A	A	A	I	I	I	T
Tributyl Phosphate	100	X	A	A	X	X	X	X	X	X	A	I	A	A	I	X	T
Trichlorobenzene	100	X	B	X	X	X	B	X	X	X	B	I	A	I	A	I	T
Trichloroethane	100	X	A	X	X	X	A	X	B	X	X	B	A	A	I	I	TV
Trichloroethylene	100	X	X	X	X	X	A	X	X	X	X	B	A	A	I	I	TV